

Product Information

VALUE PLY™

VP 202

Style: 54720

Nylon Peel/Release Ply

VP 202, Style 54720 is designed for vacuum bag lay-up composites and metal-to-metal bonding structures. The 100% Nylon 6 fiber melts at approximately 419°F (212°C). The fabric is not recommended for phenolic systems. The fabric leaves a **rough** surface impression for priming and secondary bonding. It is available in precision slit widths of 58 inches or less.

Style 54720 is available in:

FIN 060 – NAT – Scoured and Heat-Set finish

FIN 070 – SWF – Proprietary

<u>Physical Properties</u>	<u>FIN 060</u>		<u>FIN 070</u>		<u>Test Method</u>
	<u>US</u>	<u>Metric</u>	<u>US</u>	<u>Metric</u>	
Width	60 in	152.4 cm	60 in	152.4 cm	ASTM-D-3774
Length	300 yd	274.3 m	300 yd	274.3 m	
Weight	2.4 oz/yd ²	81 g/m ²	2.4 oz/yd ²	81 g/m ²	ASTM-D-3776
Finished Count					ASTM-D-3775
Warp	45 ends/in	17.7 ends/cm	40 ends/in	15.7 ends/cm	
Fill	45 picks/in	17.7 picks/cm	44 ends/in	17.3 ends/cm	
Thickness	0.006 in		0.0065 in	0.165 mm	ASTM-D-1777
Tensile Strength (Grab)					ASTM-D-5034
Warp	175 lb min	787.1 N	170 lb min	764.7 N	
Fill	175 lb min	787.1 N	170 lb min	764.7 N	
pH	4.0 – 8.0				AATCC-81
Extractable Materials	0.5% max				ASTM-D-2257 Petroleum Ether Method

The data above represents typical values for this fabric. A specification for this product has not yet been established.

For More Information, Please Contact Us:

Precision Fabrics Group, Inc.

301 North Elm Street, Suite 600

Greensboro, NC 27401

www.precisionfabrics.com

JKH 11/01/06

