



Grade 8000033 Carbon

Basis weight	1.0 oz / yd ²
Basis weight	33.9 g / m ²
Thickness	11 mil
Thickness	.28 mm
MD Tensile	17 lb/inch
CD Tensile	17 lb/inch
MD Tensile	3.0 kN / m
CD Tensile	3.0 kN / m
Binder	PVOH PVCL
Surface Resistivity	less than 15 (8) DC Ω/□
Fiber	1" mid mod PAN carbon

These are typical values taken from recent production runs and not specifications. Hollingsworth & Vose Company assumes no liability for product failure other than to supply replacement material for AFN[®] products shown to be defective when delivered. Except as stated above, there are no warranties expressed or implied on merchantability or fitness for use.

2-24-06