



1001 Trout Brook Crossing  
Rocky Hill, CT 06067-3910  
Telephone: (860) 571-5100  
FAX: (860) 571-5465

## Product Description Sheet

### FREKOTE® 44-NC

#### Mold Release Agent

Industrial Products, October 2003

#### Description

Loctite® Frekote® 44-NC should be your first choice release agent where a non-transferring release is necessary. This semi-permanent, non-migratory release system chemically bonds to the mold surface to form a micro thin film which is stable at temperatures exceeding most molding processes. Frekote 44-NC can be used for the release of epoxies, polyester resins, thermoplastics, adhesives, and rotationally molded plastics.

#### Benefits

Better mold utilization  
Non-contaminating transfer  
No mold build-up  
Significantly lower mold maintenance costs

#### Properties

Appearance	Clear liquid
Odor	Sweet Ether
Solvents	Dibutyl Ether
Specific Gravity	0.770 +/- 0.010
Shelf Life:	1 year from date of manufacture
Cured thermal stability	400° C (750°F)
Application Temp	13° C - 60° C (55°F -140°F)
Special Cautions	Moisture sensitive, keep container tightly closed when not in use. The product should always be used in a well ventilated area.

#### Mold Preparation

The mold surface must be clean and free of any release agent or other contaminants for Frekote 44-NC to be completely effective. Remove any contaminants with Frekote PMC or suitable cleaning solvent. Light industrial abrasives can be used to remove heavy resin build up.

**New Molds** Full curing of new molds is advisable to ensure the best bonding of the Frekote to the mold surface. New fiberglass and epoxy molds should be cured per manufacturer's instructions before starting production.

**Note** For porous or repaired molds, a Frekote Sealer should be used - technical data is available. Consult with your Frekote Representative for assistance.

#### Application \*Consult MSDS prior to use\*

Frekote 44-NC can be applied to mold surfaces at room temperature up to 60°C (140°F) by spraying, brushing or wiping with a clean lint-free, cloth. When spraying ensure a dry air source is used or use an airless spray system. Always use in a well ventilated area.

**Precaution** Users of closed mold systems (i.e. rotomolding) must be certain that solvent evaporation is complete and that all solvent vapors have been ventilated from the mold cavity prior to closing the mold. An oil-free compressed air source can be used to assist in evaporation of solvents and ventilation of the mold cavity.

1. Only a thin wet film is required. Wipe or spray on a smooth, thin, continuous wet film. Avoid wiping or spraying over the same area that was just coated until the solvents have evaporated. When spraying hold nozzle 8-10 inches (20-30 cm.) from mold surface. It is suggested that small areas be coated working progressively from one side of the mold to the other.
2. Initially, apply 4-6 base coats allowing 10-15 minutes between coats for solvent evaporation.
3. Curing of the final coat takes three hours at room temperature and can be shortened by baking the mold for only 15 minutes at 100-150°C (210-300°F).
4. Maximum releases will be obtained as the mold surface becomes conditioned to Frekote 44-NC. Performance is enhanced by re-coating once, after the first few initial pulls.
5. When any release difficulty is experienced, the area in question can be "touched-up" by re-coating the entire mold surface or just those areas where release difficulty is occurring. For mold temperatures above 60°C (140°F) use Frekote HMT.

**Note** Touch-up coats applied at regular intervals before the base film breaks down will extend the number of releases obtainable and reduce possible resin attack/build-up.

#### Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Loctite Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loctite Corporation's products. Loctite Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Loctite Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

NOT FOR PRODUCT SPECIFICATIONS  
THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.  
PLEASE CONTACT LOCTITE CORPORATION QUALITY DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.  
ROCKY HILL, CT FAX: +1 (860)-571-5473 DUBLIN, IRELAND FAX: +353-(1)-451-9959

Loctite and Frekote are Registered Trademarks of Loctite Corporation U.S.A.