



PRODUCT INFORMATION SHEET

Polyester Release Peel Ply Fabric

STYLE: 56030

CODE: 60002

Code 60002 is similar to 60001 except it contains black identification stripes for easy visibility. Code 60002 is designed for vacuum bag lay-up composites and metal-to-metal bonding structures. Code 60002, 100% polyester fiber melts at approximately 480°F (249°C) and is resistant to phenolic resin system degradation. The fabric leaves a medium surface impression for priming and secondary bonding. It is available in precision slit widths of less than 60 inches.

Code 60002 is available in:

FIN 060 - Natural - Scoured and Heat-Set finish

FIN 061 - SRB - Super Release Blue - An inert, heat stabilized cross-linked polymer finish.

FIN 062 - IO - International Orange for easy identification.

Physical Property	Value	Metric Equivalent	Test Method
Roll Width	60 in (min.)	152 cm	ASTM-D-3774
Roll Length	300 yds (max.)	275 m	
Weight	2.5 oz/yd ² (min.)	85 g/m ²	ASTM-D-3776
Finished Count			
Warp	70 ends/in (min.)	28 ends/cm	ASTM-D-3775
Fill	50 picks/in (min.)	19 picks/cm	
Tensile Strength (Grab)			
Warp	155 lbs. (min.)	689 Newtons	ASTM-D-5034-95
Fill	120 lbs. (min.)	534 Newtons	
Thickness	0.0055 in+ .0005 in	0.140 mm	ASTM-D-1777
pH	4.5-7.0		FTM-2811
Extractable Materials (Petroleum Ether Method)	0.5% (max.)		ASTM-D-2257

We believe the information contained in this bulletin is correct. No warranty of accuracy is implied, however, and the products and properties described herein are subject to change. The information is not to be construed as a license to operate under, nor is intended to suggest infringement of any existing patents.