



Product Data

RenShape[®] 473 FIXTURE BOARD

RenShape 473 board is a light gray, syntactic polyurethane material. This product has a density of approximately 50 lb./ft.³. RenShape 473 machines easily and finishes to a good surface.

Features of RenShape 473 board include:

ADVANTAGES	
	• Low density
	• Good dimensional stability
	• Easy to machine

ACCESSORIES	Matched Epoxy Adhesive	Polyurethane Repair Paste
	Ren-Weld [®] 103	RenCast [®] 6426-1/DT 081 Filler

ADVANTAGES*	Test Method	Test Values
Color	Visual	Light Grey
Density, lb./ft. ³ (g/cm ³)	ASTM D-792	50 (0.8)
Hardness, Shore D	ASTM D-2240	70-75
Ultimate Flexural Strength, psi (MPa)	ASTM D-790	4,000 (27.6)
Flexural Modulus, psi (MPa)	ASTM D-790	200,000 (1,379)
Ultimate Tensile Strength, psi (MPa)	ASTM D-638	2,500 (17.2)
Tg by DMA, E", °F(°C)	ASTM D-4065	212(100)
Compressive Strength, 0.2% offset, psi (MPa)	ASTM D-695	3,500 (24.1)
Compressive Modulus, psi (MPa)	ASTM D-695	210,000 (1,448)
Coefficient of Thermal Expansion -22° to 86°F, in/in/°F -30° to 30°C, in/in/°C	ASTM D-3386	30 x 10 ⁻⁶ 54 x 10 ⁻⁶

Tested @ 77°F (25°C) unless otherwise noted.

NOTE: These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Quality Control Department.

MACHINING	Roughing Speed	Roughing Feed	Finishing Speed	Finishing Feed
	1,600 RPM	40 IPM (101cm/min.)	10,000 RPM	100 IPM (254cm/min.)

Cutters: Roughing: 1 in. (2.5cm) Hog Ball End Mill 4-Flute HS Steel 8% cobalt
Finishing 5/8 in (16mm) Ball End Mill 2-Flute Carbide
Depth: Roughing varies from 0.25 in. to 2.5 in. (6mm to 6.35cm) with a 40% stepover
Finishing depth is 1/8 in. (3mm) leaving a 0.002 in. (0.05mm) scallop height

These machining parameters are represented as starting points. Cutter type and material, spindle speed, feed rate, machine power and rigidity all affect machining results. User must determine the best parameters for specific situations.

PACKAGING:

RenShape 473 board is available in a limited number of standard combinations of 2 in., 4 in., and 6 in. (5cm, 10cm, 15cm) thicknesses, width of 16 in. (40cm) and length of 60 in. (152cm). Boards are finished on top and bottom faces and on all edges. Please contact Customer Service (800) 367-8793 for currently available options, price and availability.

STORAGE/HANDLING:

Store boards flat in original cartons at 60°F to 100°F (15°C to 38°C). In accord with good industrial practice, handle with due care. Avoid dusty conditions, use adequate ventilation. Avoid breathing dust. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling.

SHELF LIFE:

Provided this material is stored under the recommended storage condition in the original container, it will remain in useable condition for an unlimited amount of time.

CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to kathy_dewey@huntsman.com.

FIRST AID!

Eyes and skin: Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation: Remove subject to fresh air.

Swallowing: Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

KEEP OUT OF REACH OF CHILDREN**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY****IMPORTANT LEGAL NOTICE:**

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

WARRANTY: Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture.

DISCLAIMER AND LIMITATION OF LIABILITY: EXCEPT AS SET FORTH ABOVE, SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Huntsman neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. **UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE.** Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Huntsman and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing **DISCLAIMER** and **LIMITATION OF LIABILITY** supercedes Buyer's documents.

WARNING: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc.
RenCast, RenShape, RenShape Solutions and Ren-Weld are registered trademarks of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.