

Advanced Materials**RenLam[®] 4014R Resin
Ren[®] 1510H Hardener****HEAT RESISTANT EPOXY LAMINATING SYSTEM**

- High Temperature Performance
- Good Work Life

DESCRIPTION :

RenLam[®] 4014R resin/Ren[®] 1510H hardener epoxy laminating system is a gray, filled, two-component material intended for use when heat resistance is required along with an extended work time. RenLam[®] 4014R resin/Ren[®] 1510H hardener epoxy is suited for continuous use at temperatures ranging from 77°F (25°C) to 300°F (149°C) after an elevated temperature postcure. Intermittent use is possible in the 300°F (149°C) to 350°F (177°C) range. RenLam[®] 4014R resin/Ren[®] 1510H hardener epoxy laminating system is well suited for use in building vacuum-form and compression molds, lay-up tools and other high-temperature tooling.

TYPICAL MIXED PROPERTIES*

<u>Property</u>	<u>4014R/1510H</u>	<u>Test Method</u>
Color, Resin	Gray	Visual
Hardener	Amber	
Mixed	Gray	
Viscosity, mixed, cP at 77°F (25°C)	5,300	ASTM-D-2393
Gel time, 14 fl. oz. at 77°F (25°C), min.	90	ASTM-D-2471

* Tested at 77°F (25°C)

MIX RATIO :

RenLam[®] 4014R resin:Ren[®] 1510H hardener 100:14 by weight

Stir each component thoroughly before use. Weight each component accurately ($\pm 5\%$) into clean containers. Thoroughly mix resin and hardener together (minimum of three minutes), scraping container sidewalls, bottom and mixing stick several times to assure a uniform mix.

TYPICAL CURED PROPERTIES :

	<u>Cure Value</u>	<u>Test-Method</u>
Specific Gravity (cast)	1.30	ASTM D-792
Cubic Inch per Pound	21.4	ASTM D-792
Hardness, Shore D	93	ASTM-D-2240
Ultimate Flexural Strength, psi (MPa)		ASTM-D-790
at 77°F (25°C)	37,200 (256)	
at 300°F (149°C)	19,800 (136)	
Flexural Modulus, psi (MPa)		ASTM-D-790
at 77°F (25°C)	1.7x10 ⁶ (11,724)	
Ultimate Tensile Strength, at 77°F (25°C), psi (MPa)	24,000 (166)	ASTM D-638
Tg by DMA, E", °F (°C)	350 (177)	ASTM D-4065
Ultimate Compressive Strength, at 77°F (25°C), psi (MPa)	26,000 (179)	ASTM D-695
Coefficient of Thermal Expansion, in./in./°F	0.83 x 10 ⁻⁶	ASTM D-3386

Cure Schedule – Contact laminate, 8 oz. glass cloth, 90° rotation, postcured 24 hrs. at 77°F (25°C), + 2 hrs. at 200°F (93°C) + 2 hrs. at 250°F (121°C) + 2 hrs. at 300°F (149°C) + 2 hrs. at 350°F (177°C), tested at 77°F (25°C).

NOTE : Typical Properties – These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Quality Control Department.

CURING INSTRUCTIONS :

With proper backup completed, allow to gel at room temperature followed by a postcure of two hours at 200°F (93°C), plus two hours at 250°F (121°C), plus two hours at 300°F (149°C), plus two hours at 350°F (177°C).

STORAGE/ SHELF LIFE :

Epoxy resins and hardeners should be stored in a dry place in their original, sealed containers at temperatures from 60-100°F (16-38°C). Material temperatures should be above 65°F (18°C) when mixing. After use, tightly reseal containers. Under these conditions, epoxy resins and hardeners will remain useable for 12 months from date of shipping from Huntsman.

CAUTION :

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to adhesives_group@huntsman.com.

FIRST AID !

Eyes and skin : Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation : Remove subject to fresh air.

Swallowing : Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Ren and RenLam are registered trademarks of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.

© 2007 Huntsman Advanced Materials Americas Inc.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

Huntsman Advanced Technology Center

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400